

Description

Crest Stripper 7 is a neutral, thickened, heavy-duty paint remover that effectively strips paint and similar organic coatings from metal surfaces. It is designed primarily for removal of epoxy, urethane and other difficult to remove coatings.

- » **Appearance:** Yellow thixotropic liquid.
- » **Cling:** Excellent on all surfaces, vertical or horizontal.
- » **Evaporation:** Self-forming surface film which retards evaporation and extends working life.
- » **Corrosion:** Non-corrosive to aluminum, magnesium, cadmium, anodized aluminum and ferrous alloys. Stripper 7 will not cause hydrogen embrittlement of high strength steel.
- » **Safety:** Non-flammable, all surfactants are biodegradable.

Specification

Crest Stripper 7 meets or exceeds:

- » MIL-R-81294D, Type I, Class 1
- » MIL-R-81294D, Type I, Class 3
- » MIL-R-81294D, Type II, Class 1

Method of Use

Application Methods

- » Spray
- » Brush

Application Instructions

- » **Concentration:** Apply full strength as received.
- » **Stripping:** Allow sufficient dwell time for thorough loosening or blistering of the paint.
- » **Rinsing:** Stripper 7 and paint residues may be rinsed with high pressure, high volume cold water or with a steam cleaning machine. Slight brushing during the rinse operation insures complete removal of all residues.
- » **Equipment:** Spray on with a non-atomizing sprayer. Product may also be applied by brush. When brush applied, daub to give a thick coat; do not brush as with paint.

Caution

Contains chlorinated solvents and phenolic bodies. Avoid contact with skin, eyes, and clothing. Use with adequate ventilation. Face shields with goggles and protective solvent-resistant gloves and clothing are required for using personnel. Stripper 7 will attack plastics; therefore, Plexiglas windows must be protected. Also, protect rubber window seals and tires. Refer to product labels and Safety Data Sheets for precautionary and handling information.

Warranty and Liability Disclaimer

The above information and recommendations concerning this product are based upon our laboratory tests and field use experience; however, since conditions of actual use are beyond our control, any recommendations, or suggestions, are made without warranty, expressed or implied. Manufacturer's and seller's sole obligation shall be to replace that portion of the product shown to be defective. Neither shall be liable for any loss, damage or injury, direct or consequential, arising out of the use of this product.